



## Technical Data Sheet

### GT-2100 One Part RTV Silicone

GT Products 2100 is a non-slump one-part silicone that cures to a tough elastomer when exposed to atmospheric moisture at room temperature. GT Products 2100 may be applied to horizontal, vertical and overhead surfaces without sagging. GT Products 2100 will adhere without a primer to many clean substrates such as aluminum, steel, glass, wood, silicone rubber, and many plastics.

GT Products 2100 features excellent resistance to heat, cold, water, ozone, and ultra-violet rays. It remains flexible and does not crack or harden. GT Products 2100 contains no solvents and has negligible shrinkage during cure. GT Products 2100 is useful over a temperature range of  $-75^{\circ}\text{F}$  to  $450^{\circ}\text{F}$  for extended operation and for intermittent periods up to  $500^{\circ}\text{F}$ . GT Products 2100 meets the requirements of 21 CFR 177.2600: Mil A-46106A, TT-S-001543A, TT-S-00230 ASTM 920-79.

#### TYPICAL PROPERTIES

##### As Supplied:

Color	white, clear, black, aluminum
Specific Gravity	1.04
Extrusion Rate (1/8 in. orifice, 90 psi)	350 gm/min.
Tack-free time ( $77^{\circ}\text{F}$ ./ 50% RH)	10 – 20 min.
Cure time 1/8 thickness ( $77^{\circ}\text{F}$ / 50%RH)	24 hr.

##### As Cured:

Durometer (Shore A)	30
Tensile, psi:	350
Elongation, %	500
Brittle Point	$-100^{\circ}\text{F}$
Volume Coefficient of Thermal Expansion, ( $32-212^{\circ}\text{F}$ )	$9.3 \times 10^{-4}$
Thermal Conductivity CAL (cm) (C)(sec)	$4.5 \times 10^{-5}$
BTU (ft) (F) (hr)	0.11
Volume Resistivity, ohm-cm	$1.5 \times 10^{15}$
Dielectric Strength, volt/mil	550
Dielectric Constant,	
60 Hz	2.8
100 KHz	2.8
Dissipation Factor	
60 Hz	0.0015
100 KHz	0.0015

## Instructions for use

GT Products 2100 will adhere to most clean surfaces without additional preparation. Mild abrasion of rubber surfaces will usually improve adhesion. A preliminary test should be made on each new substrate.

Surfaces should be thoroughly cleaned with a suitable hydrocarbon solvent such as mineral spirits, naphtha, MEK, etc. Solvents must be wiped from the surface before GT Products 2100 is applied.

GT Products 2100 cures on exposure to the moisture in air. Cure time increases with confinement and cross sectional thickness and decreases with increased humidity and temperature. Curing above 150°F will reduce physical properties. At 77°F and 50% RH GT Products 2100 will skin over and become tack-free in 10-20 minutes. Tooling and removal of masking tapes should take place prior to this time.

GT Products 2100 should be applied in a less than ¼ inch diameter bead to assure a complete cross section cure. Metal to metal bonds should not overlap more than 1 inch.

The odor given off during the cure of GT Products 2100 is acetic and disappears when fully cured.

## Caution

GT Products 2100 is not recommended for use on calcareous surfaces or on materials that bleed oils or plasticisers.

## Storage and Shelf Life

GT Products 2100 has a shelf life of 12 months when stored in the original unopened containers at or below 90°F.

## Health and Safety

GT Products 2100 is sold for industrial use only. Uncured product will irritate the eyes. In case of contact with the eye, flush with running water for 15 minutes and call physician.

Uncured GT Products 2100 may also irritate the skin. Removal by wiping with dry cloth or paper followed by washing with soap and water is recommended

GT Products 2100 releases acetic acid vapor during cure. Adequate ventilation is required. Wearing contact lenses should be avoided because vapor may be trapped behind the lenses.

The information, data, and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyers' process. SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of an product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of GT Products, Inc. or GT Products subsidiaries.