



Technical Data Sheet

GT-5090 High Performance Mold Making Silicone

GT Products® 5090 is a room temperature curing silicone rubber compound designed for the manufacture of flexible molds. This material has been designed to be used on basic shape patterns and low run molds.

GT-5090 Features

Low Viscosity

Resistance to Sulfur Based Clays

Low Durometer

GT Products® 5090 is supplied in matched kits with Catalyst 5090 designed to be used in a 10:1 ratio by weight.

Typical Properties

	Base	Catalyst
Color	White	Purple
Specific Gravity	1.12	0.98
Viscosity (cPs)	30,000	100
Mixed Viscosity	20,000	
Pot Life (Pour Time)		60-90 Minutes
After Cure (7 days @ 25°C)		
Tensile, psi:	425	
Elongation, %	550	
Durometer (Shore A)	8	
(Shore 00)	55	
Tear (die B)	110	
Linear Shrinkage; %	0.3-0.4	
Specific Gravity	1.1	

Applications:

Hobby and art projects

Foundry, sculpture , and figurines

Candle and Soap Molds

Rapid Prototyping

Special Effects

Model Making

MIXING

Because pigments can settle during storage, Catalyst 5090 should be thoroughly stirred before mixing. Use separate tools for mixing the base and catalyst to avoid cross contamination. Accurate weighing is essential to obtain maximum physical properties from the cured silicone. Add the catalyst to the base and mix until the color is uniform. Low-shear mixing of the mixture is recommended. Use clean tools and scrape the bottom and sides of the container to assure a homogeneous mixture. Avoid stirring in an excessive amount of air.

DEGASSING

Air entrapped during mixing should be removed to prevent voids in the cured product. Dearth the mixed material under a vacuum of 25 mm (29 inches) of mercury. The mixture will froth and expand to four times its original volume, crest and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing subsides.

CURING

GT Products® 5090 will cure sufficiently in 16 hours at room temperature (72°F) to be handled. GT 5090 will reach 90% of ultimate cure in 24 hours at room temperature. For full cure an additional 1-2 days at room temperature is required.

STORAGE and HANDLING

GT Products® 5090 will remain useful for six months when stored in the original unopened containers at temperatures below 80°F (27°C).

Both GT Products® 5090 and catalyst-5090 are sensitive to moisture. Keep containers covered.

Accessories:

ER-200 Mold Release

CA-5275 Fast Catalyst

GT Products Silicone Pigments

CA-5560 Ultra Fast Catalyst

The information, data, and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyers' process. SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of a product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of GT Products, Inc. or GT Products subsidiaries.

501 Industrial Blvd, Grapevine, TX 76501 • (800)221-0866 or (817)481-7113

• fax (817)421-1211 • www.gtproducts.com • info@gtproducts.com