



Technical Data Sheet

GT Products Anti-Graffiti Coatings

GT Products anti-graffiti protective coating is a clear, semi-gloss, permanent one coat silicone anti-graffiti protective coating. Our anti-graffiti coats are suitable for use over concrete, brick, stone, wood, fiberglass and pre-existing coatings. This single component, room temperature, moisture cure silicone products provide excellent durability and long service life. Intended for use over properly prepared concrete surface. Excellent cleanability with either water power-washing, or solvent wipe.

- UV resistance • Excellent adhesion • Low VOC • Fast drying • Outstanding airless spray properties
- Single component

GT Products:	GT6690	GT6691	GT6692	GT6693	GT6694
Viscosity:	6,550 cP	6,200 cP	6,000 cP	700 cP	3,100 cP
skin over time:	50 min	37 min	30 min	50 min	1 hr
tack free time:	2.5 hrs	1.5 hrs	1.5 hr	1.67 hrs	2.5 hrs
cure time:	6-8 hrs	4-6 hrs	4-6 hrs	6-8 hrs	6-8 hrs
volume solids:	94%	71%	71%	64%	94%
Solvent:	None	Naptha	Naptha	Naptha	None
Coverage: 5 mm Thickness	300 ft/gal.	230 ft/gal.	230 ft/gal.	200 ft/gal.	300 ft/gal
Coverage: 9 mm Thickness	165 ft/gal.	130 ft/gal.	130 ft/gal.	115 ft/gal.	165 ft/gal.
Appearance:	Opaque	Opaque	Translucent	Translucent	Clear
Gloss:	Semi-Gloss	Matte	Matte	Matte	Semi-Gloss
tensile:	512 psi	550 psi	555 psi	219 psi	100 psi
elong.:	131%	204%	233%	147%	140%
duro (A):	43	42	33	28	21
density:	9.6 lbs/ gal	9.24 lbs/gal	7.74 lbs/ gal	7.59 lbs/gal	8.13 lbs/ gal

The information, data, and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyers' process. SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of an product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent