



Technical Data Sheet

GT-60P High-Performance Mold Making Silicone

GT Products® 60P is a room temperature curing silicone rubber compound designed for the manufacture of flexible molds.

GT-60P Features

High Strength

Easy 10:1 mix

High Durometer

Minimal shrinkage

GT Products® 60P is supplied in matched kits with Catalyst 60P designed to be used in a 10:1 ratio by weight.

Typical Properties

	Base	Catalyst
Viscosity (cPs)	53,000	3,300
Pot Life (Pour Time)	60-90 Minutes	
After Cure (7 days @ 25°C)		
Tensile, psi:	970	
Elongation, %	110	
Durometer (Shore A)	60	
Tear (die B) minimum	130	
Linear Shrinkage; %	nil	

Applications:

Hobby and art projects	sculpture and figurines	Candle and Soap Molds
Rapid Prototyping	Special Effects	Model Making
Inventing	Rollers	Silicone Print Pads

MIXING

Because pigments can settle during storage, Catalyst 60P should be thoroughly stirred before mixing. Use separate tools for mixing the base and catalyst to avoid cross contamination. Accurate weighing is essential to obtain maximum physical properties from the cured silicone. Low-shear mixing of the mixture is recommended. Use clean tools and scrape the bottom and sides of the container to ensure a homogeneous mixture. Avoid stirring in an excessive amount of air.

DEGASSING

Air entrapped during mixing should be removed to prevent voids in the cured product. Dearth the mixed material under a vacuum of 25 mm (29 inches) of mercury. The mixture will froth and, expand four times its volume, crest and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing subsides.

CURING

GT Products® 60P will cure sufficiently in 16 hours at room temperature (72°F) to be handled. GT 60P will reach 90% of ultimate cure in 24 hours at room temperature. For full cure an additional 1-2 days at room temperature is required.

STORAGE and HANDLING

GT Products® 60P will remain useful for six months when stored in the original unopened containers at temperatures below 80°F (27°C).

Accessories:

ER-200 Mold Release

GT Products Silicone Pigments

GT-5985 Primer for adhesion to metals and other substrates

The information, data, and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyers' process. SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of a product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of GT Products, Inc. or GT Products subsidiaries.

**501 Industrial Blvd, Grapevine, TX 76501 • (800)221-0866 or (817)481-7113
• fax (817)421-1211 • www.gtproducts.com • info@gtproducts.com**