



Technical Data Sheet

GT-6265 Ultra Soft Silicone

GT Products® 6265 is an addition cure system that is very easy to use and can be used for many applications. GT-6265 when properly mixed and cured will have the feel of human skin. The translucent color will also make this silicone easy to pigment. The low viscosity makes GT-6265 easily mixed and de-aired. GT-6265 also has a quick de-mold time of approximately one hour at room temperature.

GT-6265 Features

Low Durometer	Minimal shrinkage
Fast Setting	Low Viscosity

GT Products® 6265 is supplied in matched kits with Catalyst 6265 designed to be used in a 10:1 ratio by weight.

Typical Properties

	Base	Catalyst
Color	Translucent	Translucent
Viscosity	1800	1400
Pot Life (Pour Time)	5 — 10 Minutes	

	After Cure (24 hours @ 25°C)	
Durometer	70 — 75	Sponge Scale
Linear Shrinkage; %	nil	nil
Useful Temperature Range °C (°F)	-60 — 232 (-75 — 450)	

Applications:

Hobby and art projects	Silicone Print Pads	Model Making
Rapid Prototyping	Special Effects	Rotational Casting
Inventing	Rollers	

MIXING

Because pigments can settle during storage, Catalyst 6265 should be thoroughly stirred before mixing. Use separate tools for mixing the base and catalyst to avoid cross contamination. Accurate weighing is essential to obtain maximum physical properties from the cured silicone. Add the catalyst to the base and mix until the color is uniform. Low-shear mixing of the mixture is recommended. Use clean tools and scrape the bottom and sides of the container to assure a homogeneous mixture. Avoid stirring in an excessive amount of air.

DEGASSING

Air entrapped during mixing should be removed to prevent voids in the cured product. Deair the mixed material under a vacuum of 25 mm (29 inches) of mercury. The mixture will froth and, expand four times its volume, crest and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing subsides.

CURING

GT Products® 6265 will cure sufficiently in 16 hours at room temperature (72°F) to be handled. GT 6265 will reach 90% of ultimate cure in 24 hours at room temperature. For full cure an additional 1-2 days at room temperature is required.

STORAGE and HANDLING

GT Products® 6265 will remain useful for six months when stored in the original unopened containers at temperatures below 80°F (27°C).

Accessories:

ER-200 Mold Release

GT Products Silicone Pigments

GT-5985 Primer for adhesion to metals and other substrates

The information, data, and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyers' process. SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of a product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of GT Products, Inc. or GT Products subsidiaries.