



## Technical Data Sheet

### CA-5560 Ultra-Fast Catalyst

GT Products CA-5560 is a room temperature curing silicone rubber catalyst designed to accelerate the cure of GT Products GT-5092. GT Products CA-5560 is formulated to be used in a 10:1 ratio by weight. Over catalyzing can cause the cured material to become brittle so care must be taken to make sure this catalyst is being used with the correct ratio. CA-5560 is a condensation or Tin Catalyst system. It will cure in contact with most clean dry surfaces. GT Products condensation mold making systems will cure in contact with materials such as butyl and chlorinated rubbers, sulfur containing materials, amines and other condensation RTV silicones which would inhibit the cure of addition cure systems.

#### Typical Properties

	Catalyst
Color	Red
Specific Gravity	0.98
Viscosity (cPs)	100
*Pot Life (Pour Time)	20-40 Minutes
De-mold	4-6 Hours
Storage	6 Months at Room Temperature

\* Pot life is dependent on humidity levels. Higher humidity levels will shorten the pot life.

#### Typical Uses for Condensation Silicone Systems

The information, data, and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly

Hobby and art projects	Foundry, sculpture , and figurines	Candle and Soap Molds
Rapid Prototyping	Special Effects	Model Making

declared that Seller does not guarantee the result to be obtained in Buyers' process. SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of a product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of GT Products, Inc. or GT Products subsidiaries.

**501 Industrial Blvd, Grapevine, TX 76501 • (800)221-0866 or (817)481-7113**

**• fax (817)421-1211 • [www.gtproducts.com](http://www.gtproducts.com) • [info@gtproducts.com](mailto:info@gtproducts.com)**