



Technical Data Sheet

GT-6786 Easy Knead and Cast Silicone Putty

- Our easiest material in our product line to use. Create quality silicone molds quickly and easily with little to no experience.
- You can cast a multitude of items in Easy Knead Putty including Epoxy resins, urethane resins, clays and soap.
- This is an addition cure (platinum catalyzed) system. As such, it can be heat accelerated and is subject to inhibition/poisoning by the usual factors which include (but are not limited to) sulfur, sulfur compounds and amines. Latex gloves should also not be used.
- GT6786 Easy Knead putty can be mixed with clean dry hands. If you prefer you can coat your hands with a slight amount of mineral oil or petroleum jelly but the putty should not stick to your hands.

- typical properties: cured 1:1 at room temperature (overnight – 15-24 hrs) and 625 psi

tensile	>120 psi
elongation	>130%
tear	>20 pli
durometer (A)	50

GT-6786 Features

Mix ratio	1:1
Work time at <80F	4-8 minutes [†]
Demold time	~30 minutes
Density of cured material	1.32 g/mL
Color (base/curing agent)	White/Yellow
Self-releasing	yes

Applications:

Hobby and art projects

Special Effects

Model Making

Furniture Repair

Inventing

Texture Stamping

Ear Plugs

Horse Shoeing

Jewelry Making

The information, data, and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyers' process. SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of an product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of GT Products, Inc. or GT Products subsidiaries.

501 Industrial Blvd, Grapevine, TX 76501 • (800)221-0866 or (817)481-7113
• fax (817)421-1211 • www.gtproducts.com • info@gtproducts.com